## Technical Data Sheet







#### THE MATERIAL FOR DENTAL MODELS

# PRECISA RD097 was developed in order to obtain dental models from intraoral scanning and replace the traditional gypsum model. Its major peculiarity is to be resistant to scratches.

#### **FEATURES**

- Scratchproof
- Smooth Surface
- High Resolution
- High Accuracy
- High Resistance
- Gypsum-like
- Peach Colour

#### THE PRECISA SERIES

The Precisa series includes all those materials suitable for the production of models requiring high accuracy and precision. These materials are developed and produced in-house by DWS.

#### TECHNICAL CHARACTERISTICS OF THE LIQUID MATERIAL

Environmental Values for Use	22°C - 27°C - max, RH 40% - 60%
Appearance / Colour	Liquid / Peach
Density	1,12 g/cm <sup>3</sup>
Viscosity	1100 ~ 1600 mPa•s at 25°C

### TECHNICAL CHARACTERISTICS OF THE RESIN AFTER UV CURING

Elongation at Break (%)	6~9
Hardness (Shore D)	82 ~ 86
Tensile Modulus (MPa)	30 ~ 42
Tensile Strenght (MPa)	850 ~ 1600
Flexural Strenght (MPa)	50 ~ 75
Flexural Modulus (MPa)	1200 ~ 1700
HDT @ 1.81 MPa	48 ~ 59
Application / Use	Digital Impression Models

Technical specification subject to change without notice.



